

KIXX HYDRO HD

HEAVY DUTY HYDRAULIC FLUID

DESCRIPTION

KIXX HYDRO HD formulated with Group II+ base stocks and premium anti-wear additives that provide robust protection to high pressure hydraulic system in mobile and stationary equipments. KIXX HYDRO HD has a TOST life of >4500 hours.

APPLICATIONS

- Industrial hydraulic systems of Plastic molding machines, machine tools.
- Mobile and construction equipment.
- Hydraulic systems with vane, gear or piston pumps.
- Hydraulic equipment reduction gears where EP is not required.
- Plain and antifriction bearing lubrication.
- Industrial circulating systems.

PERFORMANCE

- Denison Hydraulics HF-0 (ISO 32, 46, 68)
- Vickers M-2952-S, I-286-S [industrial applications]
- M-2950-S [mobile applications] (ISO 32, 46, 68)
- Cincinnati Milacron P-68 (ISO 32), P-69 (ISO 68), P-70 (ISO 46)
- Mannesmann Rexroth requirements (RE 07 075)
- ISO Standard 6743 Part 4, Type HM
- DIN 51524 Part 2, HLP (ISO 32, 46, 68)
- US Steel 126 and 127
- Bosch RE 90220

BENEFITS

- High protection against wear ensures longer equipment life.
- Excellent hydrolytic stability and water separability.
- Excellent protection against rust and corrosion.
- High oxidation stability provides extended oil service life.
- Good anti-foam and air-release properties ensure smooth operation and system efficiency.

ISO GRADES	32	46	68
Density, @29.5°C,(kg/liter)	0.885	0.858	0.861
Kinematic Viscosity @ 40°C (mm²/s)	32.4	45.3	67.1
Kinematic Viscosity @100°C (mm²/s)	5.6	6.8	9.1
Viscosity Index	107	106	108
Pour Point (°C)	-33	-33	-30
Flash Point (°C, COC)	221	229	235
Rust Preventing Characteristics (D665)	PASS	PASS	PASS
Oxidation Characteristics (D943)	>4500	>4500	>4500

KEY PROPERTIES

This bulletin was prepared in good faith from the best information available at the time of issue. While the values and characteristics are considered representative, some variation, not affecting performance, can be expected. It is the responsibility of the user to ensure that the products are used in the applications for which they are intended. Produced by GS Caltex Corporation.